

## Glitter

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15-20 seconds
- Peel carrier warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## Twinkle™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 15 seconds
  - ✦ If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 15 seconds
- Peel carrier warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on low setting

## Sparkle™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 10-15 seconds
- Peel carrier hot or cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on low setting

## Holographic

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15-20 seconds
- Peel carrier cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## Metal

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on low dryer setting

## StripFlock® Pro

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## Brick® 600

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 10 seconds.
- Peel carrier cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C (EasyPress® users add approx. 30°)
- Use medium/firm pressure for 20 seconds
- Peel carrier cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on low dryer setting

## Blackboard®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
  - ✦ If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15 seconds
- Peel carrier warm

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## Easy™ Puff

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Heat Press):

- Cover with Heat Transfer Cover Sheet or Multipurpose Paper
- Preheat garment for 2-3 seconds
- Apply design at 280°F/138°C
- Use medium/firm pressure for 8-10 seconds
- Peel carrier hot

### IMPORTANT APPLICATION NOTES:

Easy Puff is designed to withstand only one heat application. Repeated applications will "flatten" the puff effect permanently. It is recommended to apply Easy Puff last when used with other materials. It is not recommended for use with a home iron.

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Dry on low setting
- Do not bleach, dry clean, or use liquid fabric softener
- Wash inside out for best results

## EasyWeed®, EasyWeed® Extra, EasyWeed® Electric, EasyWeed® Glow

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- \* If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## EasyWeed® Stretch (matte)

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with firm pressure for 20 seconds
- \* If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C (EasyPress® users add approx. 30°)
- Use firm pressure for 20 seconds
- Peel carrier hot or cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal setting

## EasyWeed® Sub Block

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- \* If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot or cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 265°F / 130°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Hang item to dry

## EasyWeed® Adhesive

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- \* If areas lift after application, cover and press for 5-10 seconds.
- Peel carrier hot

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C (EasyPress® users add approx. 30°)
- Use medium pressure for 5-10 seconds
- Peel carrier hot then apply top layer

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## EasyPatterns® PLUS

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- \* If areas lift after application, cover and press for 10 seconds.
- Peel carrier hot or cold

### Application Instructions (Heat Press):

- Cut design (do not mirror). weed then mask
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold
- Cover and reheat for 2-3 seconds

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## EasyReflective®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather | Lycra®/Spandex



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- \* If areas lift after application, cover and press for 10 seconds.
- Peel carrier warm

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15 seconds
- Peel carrier warm (wait at least 15 seconds)

### Laundering:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach, dry clean, or use liquid fabric softener
- Dry on normal dryer setting

## Aurora™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



### Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 15 seconds
- Peel carrier completely cold

### Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C (EasyPress® users add approx. 30°)
- Use medium pressure for 15 seconds
- Peel carrier completely cold

### Laundering:

- Wait 24 hours before first wash
- Machine wash cold
- Tumble dry low
- Do not bleach, dry clean, or use liquid fabric softener